

POLYMER MODIFIED BITUMEN CLASS 3 PMB 25/55-65 (EUROBITUM 25-55)

USE: AT BUILDING OF HOT BITUMINOUS ROLLED PAVEMENTS

PROPERTY	UM	LIMITS		TEST METHOD
		Min.	Max.	
Penetration at 25 ⁰ C	1/10 mm	25	55	SR EN 1426-15 ASTM D 5/D5M-13
Softening point (Ring and ball)	⁰ C	65		SR EN 1427-15 ASTM D 36/D36M-14e1
Cohesion-Ductility (50 mm/min traction)	J/cm ²	NPD ^A		SR EN 13589-08 followed by SR EN 13703-04
Elastic recovery at 25 ⁰ C	%	70		SR EN 13398-10
Flash point	⁰ C	250		SR EN ISO 2592-03 ASTM D 92-16b
Fraass Break point	⁰ C		-10	SR EN 12593-15
Determination of resistance to hardening under the effect of heat and air				RTFOT Method
- mass variation ^B	%	60		SR EN 12607-1/15
- residual penetration at 25 ⁰ C	⁰ C		8	ASTM 2872-12e1
- increasing the softening point	%	-	±0,5	
-elastic recovery at 25 ⁰ C	%	60		
Storage stability				SR EN 13399-10 / SR EN 1426-15
- penetration difference at 25 ⁰ C	1/10 mm		9	ASTM D 5/D5M-13

Note: ^A NPD= No Performance Determined (Performanta nedeterminata);

^B Mass variation could be positive or negative.

Application of modified bitumen with polymers is done in accordance with the technical prescriptions:

- SR 174 -1:2009/C92:2010 “ Realization of bituminous clothing, clindred;
- SR EN 14023 -2010 National Annex – “Bitumen and bituminous binders - Framework for polymer modified bitumen specifications”

Quality control: the control is done on lot (batch)

The batch size correspond to tank capacity, max.150 tones for delivery in trucks or railroads and will consist of the same type product.

For each lot must to check all quality coefficients provided in standard specification of the product/type.

The product must to comply with all provided characteristics. If not, the lot is rejected.

In case of litigation, quality control will be made on samples taken in accordance with sampling procedure and hold for this case.

Sampling procedure: SR EN 58:2012 ASTM D 140/D140M-16

Information on product classification, packing, labelling, handling, transport and storage: according to Safety Data Sheet 87V.

The integrated Quality-Environment-Occupational Health and Safety Management System is certified by DNV-GL according to the following standards:

- ISO 9001
- ISO 14001
- BS OHSAS 18001

The test lab is accredited by RENAR, in compliance with SR EN ISO/CEI 17025.

© **ROMPETROL REFINING SA** Unauthorized reproduction by any mean, partial or total, is prohibited.

STANDARD SPECIFICATION 141

POLYMER MODIFIED BITUMEN CLASS 3 PMB 25/55-65 (EUROBITUM 25-55)