

CITOM G

USE: ANTIPHON IN THE AUTOMOBILE INDUSTRY AND IN CONSTRUCTION WORKS

PROPERTY	UM	LIMITS		TEST METHOD
		Min.	Max.	
Density at 15 ⁰ C	kg/m ³	-	910	SR EN ISO 3675-02/C91:2005 ASTM D 1298-12b(2017)
Conventional viscosity at 20 ⁰ C	⁰ E	20	-	STAS 117-87 pct.4
Appearance after drying		glossy - glass		STAS 6800-91 pct. 4.3
Adhesion: - Qualitative method		coresponds		STAS 6801-63

Quality control: the control is done on lot (batch).

The batch size correspond to tank capacity, max.150 tones for delivery in trucks or railroads and will consist of the same type product.

For each lot must to check all quality coefficients provided in standard specification of the product.

The product must to comply with all provided characteristics. If not, the lot is rejected.

In case of litigation, quality control will be made on samples taken in accordance with sampling procedure and hold for this case.

Sampling procedure: SR EN ISO 3170-2004/C91:2005/ASTM D 4057-12

Information on product classification, packing, labelling, handling, transport and storage: according to Safety Data Sheet 58V.

The integrated Quality-Environment-Occupational Health and Safety Management System is certified by DNV-GL according to the following standards:

- ISO 9001
- ISO 14001
- BS OHSAS 18001

The test lab is accredited by RENAR, in compliance with SR EN ISO/CEI 17025.

© **ROMPETROL REFINING SA** Unauthorized reproduction by any mean, partial or total, is prohibited.